



ISO 9001:2015 REGISTERED
Certificate No.: 50040 & 50415

E81T1-A1C/A1M DATA SHEET

Pinnacle Alloys E81T1-A1C/A1M

AWS CLASS E81T1-A1C, E81T1-A1M

CODE AND SPECIFICATION DATA:

AWS A5.29 ASME SFA 5.29; UNS W17031

DESCRIPTION:

Pinnacle Alloys E81T1-A1C/A1M has a nominal composition (wt-%) of 0.5 Mo. Other than the addition of Mo, the filler metal is similar to those classified in AWS A5.20. This addition increases the strength of the weld metal, especially at elevated temperatures, and provides some increase in corrosion resistance. The molybdenum however, will likely reduce the notch toughness of the weld metal. Typical applications include the welding of C-Mo base metals, such as ASTM A 161, A 204 plate, A 302 Gr A plate, and A 335-P1 pipe. Preheat and interpass temperatures are typically kept between 275-325°F. This filler metal is used in the PWHT condition, typically around 1150°F for one hour.

DIAMETERS: .045", .052", 1/16"

WELDING POSITIONS: All positions



TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)	
		100% CO ₂	75% Ar/ 25% CO ₂
Carbon (C)	0.12	0.07	0.07
Manganese (Mn)	1.25	0.85	0.96
Molybdenum (Mo)	0.40-0.65	0.45	0.55
Phosphorus (P)	0.03	0.011	0.011
Silicon (Si)	0.80	0.28	0.35
Sulfur (S)	0.03	0.009	0.009

NOTE: Single values are maximums.

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



ISO 9001:2015 REGISTERED
Certificate No.: 50040 & 50415

TYPICAL MECHANICAL PROPERTIES:

100% CO ₂ Shielding Gas	AWS Spec (min)	SR 1 HR @ 1150°F
Ultimate Tensile Strength	80,000-100,000 psi (550-690 MPa)	87,500 psi (600 MPa)
Yield Strength	68,000 psi (470 MPa)	74,300 psi (510 MPa)
Percent Elongation in 2"	19%	30%
CVN @ 72°F (20°C)	Not required	48 ft•lb _f (65 Joules)

75% Ar/ 25% CO ₂ Shielding Gas	AWS Spec (min)	SR 1 HR @ 1150°F
Ultimate Tensile Strength	80,000-100,000 psi (550-690 MPa)	89,400 psi (615 MPa)
Yield Strength	68,000 psi (470 MPa)	74,400 psi (510 MPa)
Percent Elongation in 2"	19%	31%
CVN @ 72°F (20°C)	Not required	54 ft•lb _f (72 Joules)

TYPICAL WELDING PARAMETERS:

Diameter	Position	Optimum			Amperage Range	Voltage Range
		Amperage	Voltage	WFS (ipm)		
.045"	Flat	250	28	282	100-300	21-32
	Overhead	200	26	265	150-280	21-29
	Vertical Up	200	25	265	100-230	21-28
.052"	Flat	300	28	360	100-330	19-32
	Overhead	225	26	245	150-310	21-28
	Vertical Up	225	25	245	150-280	21-27
1/16"	Flat	350	29	300	150-400	22-34
	Overhead	225	26	160	150-310	22-28
	Vertical Up	225	25	160	150-280	22-26

NOTE: Parameters reflect CO₂ shielding gas - reduce by 1-1½ volts when using 75-80% Ar/ balance CO₂. Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of steel being welded.

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.

www.pinnaclealloys.com
9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354