



ISO 9001:2015 REGISTERED
Certificate No.: 50040 & 50415

ENiFe-CI DATA SHEET

Pinnacle Alloys ENiFe-CI (55)

AWS CLASS ENiFe-CI

CODE AND SPECIFICATION DATA:

AWS A5.15 ASME SFA 5.15

DESCRIPTION:

Pinnacle Alloys ENiFe-CI is used for welding cast irons to other cast irons as well as for joining cast irons to mild steels. It is also readily used for the repair of castings. The welds are moderately hard and require carbide tipped tools for machining. A preheat and inter-pass temperature of not less than 350°F is required during welding to prevent cracking.

DIAMETERS: 3/32", 1/8", 5/32"

TYPICAL DEPOSIT COMPOSITION (Wt %):

Aluminum (Al)	0.01
Carbon (C)	0.70
Copper (Cu)	0.30
Manganese (Mn)	0.70
Nickel (Ni)	54.4
Silicon (Si)	0.10
Sulfur (S)	0.003

TYPICAL MECHANICAL PROPERTIES:

Ultimate Tensile Strength (psi)	83,000 psi
Yield Strength (psi)	59,000 psi
Percent Elongation	8%

Diameter	Length	Amperage	
		Flat	Vertical & Overhead
3/32"	12"	70-85	65-75
1/8"	14"	85-110	80-90
5/32"	14"	110-140	110-120

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



ISO 9001:2015 REGISTERED
Certificate No: 50040 & 50415

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 550 NW LeJune Road, Miami, FL 33126: OSHA Safety and Health Standards 29 CRF 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys MSDS sheet may be obtained at www.pinnaclealloys.com.

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • **1-800-856-9353** • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • **1-866-442-9353** • (602) 442-9353 • Fax (602) 442-9354