



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED  
Certificate No.: 50040 & 50415

## E10018-D2 DATA SHEET

### Pinnacle Alloys E10018-D2

AWS CLASS E10018-D2 H4R

#### CODE AND SPECIFICATION DATA:

AWS A5.5 ASME SFA 5.5; UNS W10018

#### DESCRIPTION:

Pinnacle Alloys E10018-D2 electrodes produce weld metal that contain about 1.75% Mn, 0.5% Ni, and 0.33% Mo. The weld metal from these electrodes is quite air-hardenable and usually requires preheat and PWHT. The coating is specifically formulated to resist moisture pick-up under conditions of high heat and humidity. It has quick and easy slag removal, which reduces clean up time. The low spatter level improves weld bead appearance and lends itself to higher deposition. Pinnacle Alloys E10018-D2 is primarily used for manganese-molybdenum casting, alloy forgings, structures and pressure vessel applications utilizing high-strength, low-alloy steels.

**TYPE OF CURRENT:** Direct Current Electrode Positive (DCEP) or AC

**DIAMETERS:** 3/32", 1/8", 5/32", 3/16"

**STORAGE & RECONDITIONING:** After opening, store in an oven controlled at 250°F to 400°F to ensure a low hydrogen weld deposit. If the electrode has been exposed to the atmosphere for extended periods of time, place in 250°F oven and slowly increase temperature to 600°F; bake for one hour at 600°F.

**WELDING POSITIONS:** All positions

3/16" is recommended for use in flat and horizontal positions only



**TYPICAL DIFFUSIBLE HYDROGEN BY GAS CHROMATOGRAPHY:** 3.2 ml/100g



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED  
Certificate No.: 50040 & 50415

#### TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Carbon (C)	0.15	0.05
Manganese (Mn)	1.65-2.00	1.96
Molybdenum (Mo)	0.25-0.45	0.40
Nickel (Ni)	0.90	0.47
Phosphorus (P)	0.03	0.02
Silicon (Si)	0.80	0.17
Sulfur (S)	0.03	0.01

NOTE: Single values are maximums.

#### TYPICAL MECHANICAL PROPERTIES:

	AWS Spec (min)	SR 1 HR. @ 1150°F
Ultimate Tensile Strength	100,000 psi (690 MPa)	109,000 psi (750 MPa)
Yield Strength	87,000 psi (600 MPa)	96,000 psi (661 MPa)
Percent Elongation in 2"	16%	23%
CVN @ -60°F (-50°C)	20 ft•lb <sub>f</sub> (27 Joules)	40 ft•lb <sub>f</sub> (54 Joules)

#### TYPICAL WELDING PARAMETERS:

Diameter	Type of Current	Amperage	Deposition Rate (lbs/hr)	Amperage Range	Voltage Range
3/32"	<b>DCEP or AC</b>	<b>100</b>	<b>2.35</b>	70-110	Variable
1/8"	<b>DCEP or AC</b>	<b>135</b>	<b>2.80</b>	90-160	Variable
5/32"	<b>DCEP or AC</b>	<b>170</b>	<b>4.00</b>	130-220	Variable
3/16"	<b>DCEP or AC</b>	<b>250</b>	<b>5.55</b>	200-300	Variable

**NOTE:** Optimum conditions are in boldface type. For out of position welding, decrease amperage by 15%. These values were calculated using optimum parameters and DCEP polarity. Allowance made for 2" stub loss. Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of steel being welded.

**NOTICE:** The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

**CAUTION:** Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126; OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.

SOWESCO, LLC [www.pinnaclealloys.com](http://www.pinnaclealloys.com)  
9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985  
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354