



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED
Certificate No.: 50040 & 50415

E7018-B2L (E8018-B2L) DATA SHEET

Pinnacle Alloys E7018-B2L (E8018-B2L)

AWS CLASS E7018-B2L H4R (E8018-B2L H4R)

CODE AND SPECIFICATION DATA:

AWS A5.5 ASME SFA 5.5: 2014 (1981); UNS W52118

DESCRIPTION:

Pinnacle Alloys E7018-B2L (E8018-B2L) are low-hydrogen electrodes producing weld metal that nominally contains 1.25% Cr and 0.5% Mo. They are designed to produce weld metal for high-temperature service and for matching the properties of some chromium-molybdenum base materials such as ASTM A387 Grade 11. The maximum carbon of 0.05% will improve ductility and lower hardness, it will also reduce the high temperature strength and creep resistance of the weld metal. Since all chromium-molybdenum electrodes produce weld metal which will harden in still air, both preheat and PWHT are required for most applications. In AWS A5.5-81 and previous revisions, electrodes classified as E7018-B2L were classified as E8018-B2L. The composition ranges have not been changed from A5.5-81 for the corresponding classification. The base metals with which this classification are generally used have lower strength requirements than were reflected by the former electrode classification. Therefore, unless the higher strength indicated by the former classification of this electrode is specifically necessary for a particular welding procedure, the E7018-B2L classification should be considered as identical to the corresponding E8018-B2L classification of A5.5-81. Pinnacle Alloys E7018-B2L (E8018-B2L) has quick and easy slag removal, which reduces clean up time. The low spatter level improves weld bead appearance and lends itself to higher deposition. Typical applications include boiler fabrication and maintenance.

TYPE OF CURRENT: Direct Current Electrode Positive (DCEP) or AC

DIAMETERS: 3/32", 1/8", 5/32", 3/16"

STORAGE & RECONDITIONING: After opening, store in an oven controlled at 220°F to 350°F to ensure a low hydrogen weld deposit. If the electrode has been exposed to the atmosphere for extended periods of time, place in 250°F oven and slowly increase temperature to 600°F; bake for one hour at 600°F.

WELDING POSITIONS: All positions

3/16" is recommended for use in flat and horizontal positions only



TYPICAL DIFFUSIBLE HYDROGEN BY GAS CHROMATOGRAPHY: 3.5 ml/100g

TYPICAL DEPOSIT COMPOSITION:

SOWESCO, LLC

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED
Certificate No.: 50040 & 50415

	AWS Spec	Weld Metal Analysis (%)
Carbon (C)	0.05	0.03
Chromium (Cr)	1.00-1.50	1.48
Manganese (Mn)	0.90	0.63
Molybdenum (Mo)	0.40-0.65	0.53
Phosphorus (P)	0.03	0.014
Silicon (Si)	0.80	0.56
Sulfur (S)	0.03	0.01

NOTE: Single values are maximums.

TYPICAL MECHANICAL PROPERTIES:

	AWS Spec (min)	SR 1 HR. @ 1275°F
Ultimate Tensile Strength	75,000 psi (520 MPa)	89,000 psi (612 MPa)
Yield Strength	57,000 psi (390 MPa)	74,000 psi (510 MPa)
Percent Elongation in 2"	19%	28%

		As Welded
CVN @ -20°F (-30°C)	Not required	46 ft•lb _f (62 Joules)
CVN @ -40°F (-40°C)	Not required	30 ft•lb _f (41 Joules)

TYPICAL WELDING PARAMETERS:

Diameter	Type of Current	Amperage	Deposition Rate (lbs/hr)	Amperage Range	Voltage Range
3/32"	DCEP or AC	100	2.51	70-110	Variable
1/8"	DCEP or AC	135	3.66	90-160	Variable
5/32"	DCEP or AC	170	4.06	130-220	Variable
3/16"	DCEP or AC	250	5.88	200-300	Variable

NOTE: Optimum conditions are in boldface type. For out of position welding, decrease amperage by 15%. These values were calculated using optimum parameters and DCEP polarity. Allowance made for 2" stub loss. Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of steel being welded.

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126; OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.

SOWESCO, LLC www.pinnaclealloys.com
9384 Wallisville Road • Houston, Texas 77013 • **1-800-856-9353** • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • **1-866-442-9353** • (602) 442-9353 • Fax (602) 442-9354