

## Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED Certificate No.: 50040 & 50415

# **ENICrMo-4 DATA SHEET**

Pinnacle Alloys ENiCrMo-4 (C276)
AWS CLASS ENiCrMo-4
CODE AND SPECIFICATION DATA:
AWS A5.11 ASME SFA 5.11: UNS W80276

## **DESCRIPTION:**

Pinnacle Alloys ENiCrMo-4 has a nominal composition (wt.-%) of 57 Ni, 16 Mo, 15.5 Cr, 5.5 Fe, 4 W, low C. Electrodes of this classification are used for welding low carbon nickel-chromium-molybdenum alloy, for welding the clad side of joints in steel clad with low carbon nickel-chromium-molybdenum alloy, and for welding low carbon nickel-chromium-molybdenum alloy to steel and to other nickel-base alloys. Typical specifications for the nickel-chromium-molybdenum base metals are ASTM B 574, B 575, B 619, B 622, and B 626, all of which have UNS Number N10276. Pinnacle Alloys ENiCrMo-4 offers exceptional resistance to pitting and crevice corrosion. This electrode is formulated to work well in harsh environments as well as pipelines, pressure vessels, chemical processing plants, and oil and gas facilities.

**TYPE OF CURRENT:** Direct Current Electrode Positive (DCEP)

**DIAMETERS:** 3/32", 1/8", 5/32", 3/16"

**WELDING POSITIONS:** All positions

5/32" & 3/16" recommended for use in flat & horizontal positions only













## Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED Certificate No.: 50040 & 50415

## TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Carbon (C)	0.02	0.01
Chromium (Cr)	14.5-16.5	15.7
Cobalt (Co)	2.50	0.70
Copper (Cu)	0.50	0.04
Iron (Fe)	4.0-7.0	6.20
Manganese (Mn)	1.00	0.30
Molybdenum (Mo)	15.0-17.0	15.6
Nickel (Ni)	Balance	57.5
Phosphorus (P)	0.04	0.01
Silicon (Si)	0.2	0.18
Sulfur (S)	0.03	0.007
Tungsten (W)	3.0-4.5	3.50
Vanadium (V)	0.35	0.14

NOTE: Single values are maximums.

### **TYPICAL MECHANICAL PROPERTIES:**

	AWS Spec (min)	As Welded	
Ultimate Tensile Strength	100,000 psi (690 MPa)	104,000 psi (720 MPa)	
Percent Elongation in 2"	25%	40%	

#### TYPICAL WELDING PARAMETERS:

Diameter	Type of Current	Amperage Range		Voltago Bango
		Flat	Out of Position	Voltage Range
3/32"	DCEP	70-90	65-80	20-23
1/8"	DCEP	80-110	75-95	21-24
5/32"	DCEP	120-160	Not recommended	22-25
3/16"	DCEP	170-190	Not recommended	23-26

NOTE: Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of material being welded.

**NOTICE:** The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

**CAUTION:** Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CRF 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.

SOWESCO, LLC www.pinnaclealloys.com 9384 Wallisville Road • Houston, Texas 77013 • **1-800-856-9353** • (713) 688-9353 • Fax (713) 688-6985 2602 S. 50th Avenue • Phoenix, Arizona 85043 • **1-866-442-9353** • (602) 442-9353 • Fax (602) 442-9354