



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED  
Certificate No.: 50040 & 50415

## ER630 DATA SHEET

### Pinnacle Alloys ER630

AWS CLASS ER630

#### CODE AND SPECIFICATION DATA:

AWS A5.9 ASME SFA 5.9; UNS S17480

#### DESCRIPTION:

Pinnacle Alloys ER630 has a nominal composition (wt.-%) of 16.4 Cr, 4.7 Ni, 3.6 Cu. The composition is designed primarily for welding ASTM A 564 Type 630 and some other precipitation-hardening stainless steels. The composition is modified to prevent the formation of ferrite networks in the martensitic microstructure which have deleterious effect on mechanical properties. Dependent on the application and weld size, the weld may be used as welded; welded and precipitation hardened; or welded, solution treated, and precipitation hardened.

**DIAMETERS:** .030", .035", .045", 1/16", 3/32", 1/8", 5/32"

**WELDING POSITIONS:** GTAW & GMAW: All positions



#### TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Carbon (C)	0.05	0.013
Chromium (Cr)	16.0-16.75	16.21
Copper (Cu)	3.25-4.00	3.35
Manganese (Mn)	0.25-0.75	0.43
Molybdenum (Mo)	0.75	0.07
Nickel (Ni)	4.50-5.00	4.60
Nitrogen (N)	N.S.*	0.030
Phosphorus (P)	0.03	0.020
Silicon (Si)	0.75	0.39
Sulfur (S)	0.03	0.001
Niobium (Nb) + Tantalum (Ta)	0.15-0.30	0.07

\*N.S. means Not Specified.

NOTE: Single values are maximums.

SOWESCO, LLC

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985  
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED  
Certificate No.: 50040 & 50415

#### FERRITE NUMBER AND PITTING RESISTANCE EQUIVALENT NUMBER:

To obtain Ferrite Numbers or PRE<sub>N</sub>, please contact SOWESCO technical support at the number below.

#### TYPICAL WELDING PARAMETERS:

	Diameter	Amperage	Volts	Shielding Gas
<b>GTAW</b>	1/16"	80-110		100% Ar
	3/32"	90-130		
	1/8"	120-175		
	5/32"	150-220		
<b>GMAW</b> Spray Transfer	.030"	130-200	23-27	98% Ar/ 2% O <sub>2</sub> (35 cfh)
	.035"	150-225	23-26	
	.045"	200-325	24-28	
	1/16"	300-350	24-27	
<b>GMAW</b> Short-Circuit	.030"	50-150	14-20	90% He/ 7½% Ar/ 2½% CO <sub>2</sub> (25 cfh)
	.035"	60-200	14-22	
	.045"	75-225	15-23	
	1/16"	100-250	16-23	
<b>SAW</b>	3/32"	275-350	28-30	Suitable Flux
	1/8"	350-450	29-32	

**NOTE:** Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of material being welded.

**NOTICE:** The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

**CAUTION:** Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.