



Pinnacle Alloys are products of SOWESCO

ISO 9001:2015 REGISTERED  
Certificate No.: 50040 & 50415

## ERNiCrCoMo-1 DATA SHEET

### Pinnacle Alloys ERNiCrCoMo-1 (617)

AWS CLASS ERNiCrCoMo-1

#### CODE AND SPECIFICATION DATA:

AWS A5.14 ASME SFA 5.14; UNS N06617

#### DESCRIPTION:

Pinnacle Alloys ERNiCrCoMo-1 has a nominal composition (wt.-%) of 53 Ni, 23 Cr, 12 Co, 9 Mo, 1 Fe. Filler metal of this classification is used for welding nickel-chromium-cobalt-molybdenum alloy (UNS Number N06617) to itself using the GTAW, GMAW, and SAW processes. Pinnacle Alloys ERNiCrCoMo-1 provides excellent strength and oxidation resistance from 1500°F up to 2100°F.

**DIAMETERS:** .035", .045", 1/16", 3/32", 1/8", 5/32"

**WELDING POSITIONS:** GTAW & GMAW: All positions



#### TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Aluminum (Al)	0.8-1.5	1.23
Carbon (C)	0.05-0.15	0.07
Chromium (Cr)	20.0-24.0	22.69
Cobalt (Co)	10.0-15.0	11.35
Copper (Cu)	0.50	0.08
Iron (Fe)	3.00	0.47
Manganese (Mn)	1.00	0.31
Molybdenum (Mo)	8.0-10.0	8.85
Nickel (Ni)	Balance	53.9
Phosphorus (P)	0.03	0.005
Silicon (Si)	1.00	0.27
Sulfur (S)	0.015	0.002
Titanium (Ti)	0.60	0.36

NOTE: Single values are maximums.

SOWESCO, LLC

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985  
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



Pinnacle Alloys are products of SOWESCO

ISO 9001:2015 REGISTERED  
Certificate No.: 50040 & 50415

#### TYPICAL MECHANICAL PROPERTIES:

	AWS Spec (min)	As Welded
Ultimate Tensile Strength	Not required	100,000 psi (690 MPa)
Percent Elongation in 2"	Not required	45%

#### TYPICAL WELDING PARAMETERS:

	Diameter	Amperage	Volts	Shielding Gas
GTAW	1/16"	90-130		100% Ar
	3/32"	120-175		
	1/8"	150-220		
GMAW	.035"	150-190	26-29	75% Ar/ 25% He
	.045"	180-220	28-32	
	1/16"	200-250	29-33	
SAW	3/32"	275-350	28-30	Suitable Flux
	1/8"	350-450	29-32	
	5/32"	400-550	30-33	

**NOTE:** Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of material being welded.

**NOTICE:** The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

**CAUTION:** Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.