



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED
Certificate No.: 50040 & 50415

ERNiCrMo-4 DATA SHEET

Pinnacle Alloys ERNiCrMo-4 (C276)

AWS CLASS ERNiCrMo-4

CODE AND SPECIFICATION DATA:

AWS A5.14 ASME SFA 5.14; UNS N10276

DESCRIPTION:

Pinnacle Alloys ERNiCrMo-4 has a nominal composition (wt.-%) of 57 Ni, 16 Cr, 15.5 Mo, 5.5 Fe, and 4 W. Filler metal of this classification is used for welding nickel-chromium-molybdenum alloy (ASTM B 574, B 575, B 619, B 622, and B 628 having UNS Number N10276) to itself, to steel, to other nickel-based alloys, and for cladding steel with nickel-chromium-molybdenum weld metal using the GTAW and GMAW processes. Pinnacle Alloys ERNiCrMo-4 provides excellent corrosion resistance in many harsh conditions and is particularly resistant to crevice corrosion and pitting. This wire is well suited for pipelines, pressure vessels, chemical processing plants, offshore oil and gas facilities, and marine environments.

DIAMETERS: .035", .045", 1/16", 3/32", 1/8", 5/32"

WELDING POSITIONS: GTAW & GMAW: All positions



TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Carbon (C)	0.02	0.006
Chromium (Cr)	14.5-16.5	15.63
Cobalt (Co)	2.50	0.03
Copper (Cu)	0.50	0.04
Iron (Fe)	4.0-7.0	5.75
Manganese (Mn)	1.00	0.50
Molybdenum (Mo)	15.0-17.0	15.86
Nickel (Ni)	Balance	57.8
Phosphorus (P)	0.04	0.005
Silicon (Si)	0.08	0.04
Sulfur (S)	0.03	0.001
Tungsten (W)	3.0-4.5	3.78

SOWESCO, LLC

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



Pinnacle Alloys are products of SOWESCO

ISO 9001:2008 REGISTERED
Certificate No.: 50040 & 50415

Vanadium (V)	0.35	0.04
--------------	------	------

NOTE: Single values are maximums.

TYPICAL MECHANICAL PROPERTIES:

	AWS Spec (min)	As Welded
Ultimate Tensile Strength	Not required	108,000 psi (750 MPa)
Percent Elongation in 2"	Not required	42%

TYPICAL WELDING PARAMETERS:

	Diameter	Amperage	Volts	Shielding Gas
GTAW	1/16"	90-130		100% Ar
	3/32"	120-175		
	1/8"	150-220		
GMAW	.035"	150-190	26-29	75% Ar/ 25% He
	.045"	180-220	28-32	
	1/16"	200-250	29-33	
SAW	3/32"	275-350	28-30	Suitable Flux
	1/8"	350-450	29-32	
	5/32"	400-550	30-33	

NOTE: Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of material being welded.

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.