



Pinnacle Alloys are products of SOWESCO

ISO 9001:2015 REGISTERED
Certificate No.: 50040 & 50415

PREMIER S-3 DATA SHEET

Pinnacle Alloys Premier S-3

AWS CLASS ER70S-3

CODE AND SPECIFICATION DATA:

AWS A5.18 ASME SFA 5.18; UNS K11022

DESCRIPTION:

Pinnacle Alloys Premier S-3 is used for single-pass and multipass applications. Typical specifications for these steels are ASTM A 36, A 285-C, A 515-55, and A 516-70, which have UNS Numbers K02600, K02801, K02001, and K02700, respectively.

DIAMETERS: .035", .045"

WELDING POSITIONS: All positions

Spray Transfer is recommended for use in flat position and for and horizontal fillet welds.



TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Carbon (C)	0.06-0.15	0.070
Chromium (Cr)	0.15	0.024
Copper (Cu)	0.50	0.15
Manganese (Mn)	0.9-1.4	1.07
Molybdenum (Mo)	0.15	0.004
Nickel (Ni)	0.15	0.010
Phosphorus (P)	0.025	0.012
Silicon (Si)	0.45-0.75	0.62
Sulfur (S)	0.035	0.011
Vanadium (V)	0.03	0.003

NOTE: Single values are maximums.

SOWESCO, LLC

www.pinnaclealloys.com

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



Pinnacle Alloys are products of SOWESCO

ISO 9001:2015 REGISTERED
Certificate No.: 50040 & 50415

TYPICAL MECHANICAL PROPERTIES:

	AWS Spec (min)	As Welded
Ultimate Tensile Strength	70,000 psi (480 MPa)	79,936 psi (551 MPa)
Yield Strength	58,000 psi (400 MPa)	64,150 psi (442 MPa)
Percent Elongation in 2"	22%	28%
CVN @ 0°F (-20°C)	20 ft•lb _f (27 Joules)	62 ft•lb _f (84 Joules)

TYPICAL WELDING PARAMETERS:

	Diameter	Amperage	Volts	Shielding Gas
GMAW Spray Transfer	.035"	280-320	27-30	98% Ar/ 2% O ₂
	.045"	300-360	27-29	
GMAW Short-Circuit	.035"	140-200	16-20	75% Ar/ Balance CO ₂
	.045"	160-280	18-30	

NOTE: For out of position welding, decrease amperage by 15%. Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of steel being welded.

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.