



ISO 9001:2015 REGISTERED  
Certificate No.: 50040 & 50415

## R60 DATA SHEET

### Pinnacle Alloys R60

AWS CLASS R60

#### CODE AND SPECIFICATION DATA:

AWS A5.2 ASME SFA 5.2; UNS K00060

#### DESCRIPTION:

Pinnacle Alloys R60 welding rods are used for the oxyfuel gas welding of steels, where the minimum tensile strength requirement of the steel does not exceed 60,000 psi. R60 rods have a low carbon steel composition. Oxyfuel gas welding rods have no coverings to influence the usability of the rod. Thus, the ability to weld in the vertical or overhead position is essentially a matter of welder skill and can be affected to some degree by the chemical composition of the rod.

**DIAMETERS:** 1/16", 3/32", 1/8", 5/32"

**WELDING POSITIONS:** All positions



#### TYPICAL DEPOSIT COMPOSITION:

	AWS Spec	Weld Metal Analysis (%)
Aluminum (Al)	0.02	0.005
Carbon (C)	0.15	0.101
Chromium (Cr)	0.20	0.070
Copper (Cu)	0.30	0.240
Manganese (Mn)	0.90-1.40	0.930
Molybdenum (Mo)	0.20	0.027
Nickel (Ni)	0.30	0.100
Phosphorus (P)	0.035	0.013
Silicon (Si)	0.10-0.35	0.170
Sulfur (S)	0.035	0.016

NOTE: Single values are maximums.

[www.pinnaclealloys.com](http://www.pinnaclealloys.com)

9384 Wallisville Road • Houston, Texas 77013 • 1-800-856-9353 • (713) 688-9353 • Fax (713) 688-6985  
2602 S. 50th Avenue • Phoenix, Arizona 85043 • 1-866-442-9353 • (602) 442-9353 • Fax (602) 442-9354



ISO 9001:2015 REGISTERED  
Certificate No.: 50040 & 50415

**TYPICAL MECHANICAL PROPERTIES:**

	<b>AWS Spec (min)</b>	<b>As Welded</b>
Ultimate Tensile Strength	60,000 psi (400 MPa)	75,420 psi (520 MPa)
Percent Elongation in 2"	20%	24%

**NOTICE:** The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

**CAUTION:** Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CRF 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.

[www.pinnaclealloys.com](http://www.pinnaclealloys.com)

9384 Wallisville Road • Houston, Texas 77013 • **1-800-856-9353** • (713) 688-9353 • Fax (713) 688-6985  
2602 S. 50th Avenue • Phoenix, Arizona 85043 • **1-866-442-9353** • (602) 442-9353 • Fax (602) 442-9354