



PREMIER 71 DATA SHEET

Pinnacle Alloys Premier 71 (E71T-1C)

AWS CLASS E71T-1C

CODE AND SPECIFICATION DATA:

AWS A5.20 ASME SFA 5.20; UNS W07601

DESCRIPTION:

Pinnacle Alloys Premier 71 (E71T-1C) is a carbon steel electrode designed for single and multipass welding of carbon steels. These electrodes are designed for use with DCEP power sources. They are characterized by a spray transfer, low spatter loss, flat to slightly convex bead contour, and a moderate volume of slag which completely covers the weld bead. These electrodes have a rutile base slag and have the ability to produce high deposition rates. Typical applications include ship building, machinery, and bridges. Typical base metal specifications for these steels are ASTM A 36, A 106 Gr B, A 516 Gr 60, and materials with similar composition and strength.

DIAMETERS: .035", .045", .052", 1/16"**WELDING POSITIONS:** All positions**TYPICAL DEPOSIT COMPOSITION:**

	AWS Spec	Weld Metal Analysis (%)
		100% CO ₂
Carbon (C)	0.12	0.04
Manganese (Mn)	1.75	1.29
Phosphorus (P)	0.03	0.01
Silicon (Si)	0.90	0.49
Sulfur (S)	0.03	0.009

NOTE: Single values are maximums.



AN ISO 9001:2015 COMPANY
CERTIFICATE NO.: C755336

TYPICAL MECHANICAL PROPERTIES:

	AWS Spec (min)	As Welded
Ultimate Tensile Strength	70,000-95,000 psi (490-670 MPa)	84,200 psi (580 MPa)
Yield Strength	58,000 psi (390 MPa)	79,000 psi (550 MPa)
Percent Elongation in 2"	22%	28%
CVN @ 0°F (-20°C)	20 ft•lb _f (27 Joules)	37 ft•lb _f (50 Joules)
CVN @ 32°F (0°C)	Not required	63 ft•lb _f (86 Joules)

TYPICAL WELDING PARAMETERS:

Diameter	Position	Optimum			Amperage Range	Voltage Range
		Amperage	Voltage	WFS (ipm)		
.045"	Flat	250	28	282	120-300	21-32
	Overhead	200	26	265	150-280	21-29
	Vertical Up	200	25	265	120-230	21-28
.052"	Flat	300	28	360	120-330	19-32
	Overhead	225	26	245	150-310	21-28
	Vertical Up	225	25	245	150-280	21-27
1/16"	Flat	350	29	300	150-400	22-34
	Overhead	225	26	160	150-310	22-28
	Vertical Up	225	25	160	150-280	22-27

NOTE: Properties and parameters reflect CO₂ shielding gas. Maintaining a proper welding procedure, including pre-heat and interpass temperatures, may be critical depending on the type and thickness of steel being welded.

NOTICE: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for the use in the field. The manufacturer disclaims any warranty of merchantability of fitness for any particular purpose with respect to its products.

CAUTION: Consumers should be thoroughly familiar with the safety precautions on the warning label posted in each shipment and in the American National Standards A49.1, "Safety in Welding and Cutting," published by the American Welding Society, 8669 NW 36 Street, #130, Miami, FL 33126: OSHA Safety and Health Standards 29 CFR 1910 is available from the U.S. Department of Labor, Washington, D.C. 20210.

Pinnacle Alloys SDS sheets may be obtained on the website below.